

Dark Emperador

Physico-Mecanical Properties

Volumetric weight:	2.65 gr/cm ³
Coefficient of absorption:	0.40 %
Porosity:	1.20 %
Compression strength:	1,597 kg/cm ²
Flexure Strength:	210 kg/cm ²
Frictional wear test:	0.55 cm
Impact Strength:	35 cm
Knoop microhardness:	180 kg/mm ²